

H-LaK54			734515				n _d = 1.734000		v _d = 51.49		n _F - n _C = 0.014256	
							n _e = 1.737396		v _e = 51.25		n _{F'} - n _{C'} = 0.014389	
折射率 Refractive Index			相对部分色散 Relative Partial Dispersions				内部透射率 Internal Transmittance T					
	λ (nm)		P _{s,t}	0.2751	P' _{s,t}	0.2726	λ (nm)	τ (5mm)	τ (10mm)			
n _{2325.42}	2325.42	1.693824	P _{C,s}	0.5315	P' _{C',s}	0.5743	2400	0.810	0.650			
n _{1970.09}	1970.09	1.701236	P _{d,C}	0.3027	P' _{d,C'}	0.2522	2200	0.948	0.899			
n _{1529.58}	1529.58	1.709087	P _{e,d}	0.2382	P' _{e,d}	0.2360	2000	0.981	0.962			
n _{1060.0}	1060.0	1.717247	P _{g,F}	0.5495	P' _{g,F'}	0.4875	1800	0.992	0.985			
n _t	1013.98	1.718186	P _{i,h}	0.7875	P' _{i,h}	0.7802	1600	0.998	0.997			
n _s	852.11	1.722108	异常色散 Abnormal Dispersions				1400	0.999	0.998			
n _r	706.52	1.727238					ΔP _{C,t}	0.0177	ΔP _{C,s}	0.0080	1200	0.999
n _C	656.27	1.729685	ΔP _{F,e}	-0.0024	ΔP _{g,F}	-0.0086	1060	0.999	0.998			
n _{C'}	643.85	1.730371	着色度 Color Code				1000	0.999	0.998			
n _{He-Ne}	632.8	1.731011					λ ₈₀ /λ ₅	365/275		950	0.999	0.998
n _D	589.29	1.733873	λ ₇₀ /λ ₅			900	0.999	0.998				
n _d	587.56	1.734000	热性质 Thermal Properties				850	0.998	0.997			
n _e	546.07	1.737396					T _g (°C)	639		800	0.998	0.996
n _F	486.13	1.743941	T _s (°C)	676		700	0.997	0.995				
n _{F'}	479.99	1.744760	T ₁₀ ^{14.5} (°C)	597		650	0.997	0.994				
n _g	435.83	1.751774	T ₁₀ ¹³ (°C)	626		600	0.997	0.994				
n _h	404.66	1.758314	T ₁₀ ^{7.6} (°C)	729		550	0.997	0.994				
n _i	365.01	1.769541	α _{30/70} (10 ⁻⁷ /K)	51		500	0.996	0.992				
n _{313.18}	313.18	1.792663	α _{100/300} (10 ⁻⁷ /K)	74		480	0.995	0.990				
n _{302.15}	302.15	1.799588	λ[W/(m·K)]			460	0.993	0.987				
色散公式常数 Constants of Dispersion Formula			化学性质 Chemical Properties				440	0.992	0.984			
							K ₁	1.20772937E+00		Grade	420	0.989
L ₁	1.76389155E-02		D _w	1		400	0.984	0.969				
K ₂	7.37418371E-01		D _A	3		390	0.978	0.957				
L ₂	6.66515982E-04		CR	1		380	0.969	0.938				
K ₃	1.35749026E+00		RC(S)	1		370	0.951	0.905				
L ₃	9.69938806E+01		RA(S)	3		360	0.924	0.853				
折射率温度系数常数 Constants of dn/dt			机械性质 Mechanical Properties				350	0.880	0.780			
							D ₀	5.91E-06		H _k (10 ⁷ Pa)	770	
D ₁	1.71E-08		折射率温度系数 Temperature Coefficients of Refractive Index				330	0.730	0.530			
D ₂	-2.96E-11						dn/dt relative(10 ⁻⁶ /°C)		320	0.620	0.390	
E ₀	5.65E-07		温度范围 (°C)	t	C'	d	e	F'	g	310	0.490	0.240
E ₁	5.05E-10		-60~-40	4.7	5.2	5.4	5.6	6.1	6.6	300	0.350	0.120
λ _{TK} (μm)	0.196		-40~-20	4.8	5.3	5.6	5.7	6.3	6.8	290	0.200	0.040
其他性质 Other Properties			0~-20	5.1	5.4	5.7	5.9	6.5	7.0	ρ (g/cm ³)		
			20~40	5.4	5.8	6.0	6.4	6.7	7.4	4.01		
备注 Remarks			20~40	5.5	6.1	6.4	6.7	7.1	7.6			
			40~60	5.6	6.2	6.5	6.7	7.2	7.7			
			60~80	5.6	6.2	6.5	6.7	7.2	7.7			
			80~100	5.8	6.5	6.6	7.0	7.5	8.0			
			100~120	5.9	6.7	6.9	7.3	7.7	8.4			
			120~140	6.3	7.1	7.5	7.6	8.3	8.9			