

H-QF6A			532488			n _d = 1.531720		v _d = 48.84		n _F - n _C = 0.010887	
						n _e = 1.534305		v _e = 48.53		n _{F'} - n _{C'} = 0.011009	
折射率 Refractive Index			相对部分色散 Relative Partial Dispersions				内部透射率 Internal Transmittance T				
	λ (nm)		P _{s,t}	0.2648	P' _{s,t}	0.2619	λ (nm)	τ (5mm)	τ (10mm)		
n _{2325.42}	2325.42	1.502566	P _{C,s}	0.5185	P' _{C',s}	0.5595	2400	0.942	0.888		
n _{1970.09}	1970.09	1.507783	P _{d,C}	0.2991	P' _{d,C'}	0.2490	2200	0.945	0.893		
n _{1529.58}	1529.58	1.513362	P _{e,d}	0.2374	P' _{e,d}	0.2348	2000	0.986	0.973		
n _{1060.0}	1060.0	1.519250	P _{g,F}	0.5662	P' _{g,F'}	0.5020	1800	0.990	0.981		
n _t	1013.98	1.519936	P _{i,h}	0.8642	P' _{i,h}	0.8547	1600	0.994	0.989		
n _s	852.11	1.522819	异常色散 Abnormal Dispersions				1400	0.993	0.986		
n _r	706.52	1.526631					ΔP _{C,t}	0.0069	ΔP _{C,s}	0.0013	1200
n _C	656.27	1.528464	ΔP _{F,e}	0.0005	ΔP _{g,F}	0.0037	1060	0.999	0.998		
n _{C'}	643.85	1.528979	着色度 Color Code				1000	0.999	0.998		
n _{He-Ne}	632.8	1.529462					λ ₈₀ /λ ₅	360/340			950
n _D	589.29	1.531624	λ ₇₀ /λ ₅				900	0.999	0.998		
n _d	587.56	1.531720	热性质 Thermal Properties				850	0.999	0.998		
n _e	546.07	1.534305					T _g (°C)	513			800
n _F	486.13	1.539351	T _s (°C)	582			700	0.997	0.994		
n _{F'}	479.99	1.539988	T ₁₀ ^{14.5} (°C)	458			650	0.996	0.993		
n _g	435.83	1.545515	T ₁₀ ¹³ (°C)	501			600	0.997	0.995		
n _h	404.66	1.550792	T ₁₀ ^{7.6} (°C)	677			550	0.998	0.996		
n _i	365.01	1.560201	α _{30/70°C} (10 ⁻⁷ /K)	86			500	0.997	0.994		
n _{313.18}	313.18		α _{100/300°C} (10 ⁻⁷ /K)	95			480	0.997	0.994		
n _{302.15}	302.15		λ[W/(m·K)]				460	0.997	0.994		
色散公式常数 Constants of Dispersion Formula			化学性质 Chemical Properties				440	0.995	0.991		
							K ₁	8.30014908E-02		Grade	
L ₁	4.93974056E-02		D _w	1			400	0.995	0.990		
K ₂	1.22223237E+00		D _A	1			390	0.991	0.983		
L ₂	8.30688707E-03		CR	1			380	0.986	0.972		
K ₃	1.01475439E+00		RC(S)	1			370	0.970	0.941		
L ₃	1.14773547E+02		RA(S)	1			360	0.909	0.826		
折射率温度系数常数 Constants of dn/dt			机械性质 Mechanical Properties				350	0.703	0.494		
							D ₀	-5.28E-06		H _k (10 ⁷ Pa)	521
D ₁	2.18E-08		折射率温度系数 Temperature Coefficients of Refractive Index				330				
D ₂	-9.29E-11						温度范围 (°C) dn/dt relative(10 ⁻⁶ /°C)				320
E ₀	4.95E-07		Range of Temperature	t	C'	d					e
E ₁	4.67E-10		-60~-40							E (10 ⁷ Pa)	6519
λ _{TK} (μm)	0.262		-40~-20	-1.2	-1.0	-0.7	-0.3	-0.4	0.3	G (10 ⁷ Pa)	2646
其他性质 Other Properties			-20~0	-1.1	-0.8	-0.5	-0.3	0.2	0.6	μ	0.232
			0~20	-0.7	-0.5	-0.3	-0.1	0.2	0.7	B (10 ⁻¹² /Pa)	2.94
备注 Remarks			20~40	-0.6	-0.3	0.0	0.2	0.7	1.0		
			40~60	-0.4	0.1	0.4	0.5	0.8	1.3		
ρ (g/cm ³)			60~80	-0.5	0.0	0.0	0.1	0.8	1.4		
			80~100								
ρ (g/cm ³)			100~120								
			120~140								