

H-ZLaF68B			883408		$n_d = 1.88300$	$v_d = 40.79$	$n_F - n_C = 0.021640$			
					$n_e = 1.88815$	$v_e = 40.56$	$n_F - n_C' = 0.021897$			
<b>折射率 Refractive Index</b>			<b>相对部分色散 Relative Partial Dispersions</b>				<b>内部透射率 Internal Transmittance T</b>			
	$\lambda$ (nm)		$P_{s,t}$	0.2375	$P'_{s,t}$	0.2347	$\lambda$ (nm)	$\tau$ (5mm)	$\tau$ (10mm)	
$n_{2325.42}$	2325.42		$P_{C,s}$	0.5014	$P'_{C',s}$	0.5416	2400	0.913	0.833	
$n_{1970.09}$	1970.09		$P_{d,C}$	0.2971	$P'_{d,C'}$	0.2475	2200	0.976	0.952	
$n_{1529.58}$	1529.58		$P_{e,d}$	0.2380	$P'_{e,d}$	0.2352	2000	0.989	0.979	
$n_{1060.0}$	1060.0		$P_{g,F}$	0.5695	$P'_{g,F'}$	0.5049	1800	0.996	0.993	
$n_t$	1013.98	1.86058	$P_{i,h}$		$P'_{i,h}$		1600	0.998	0.997	
$n_s$	852.11	1.86572	<b>异常色散 Abnormal Dispersions</b>				1400	0.999	0.998	
$n_r$	706.52	1.87299	$\Delta P_{C,t}$	0.0004	$\Delta P_{C,s}$	0.0032	1200	0.999	0.998	
$n_C$	656.27	1.87657	$\Delta P_{F,e}$	-0.0025	$\Delta P_{g,F}$	-0.0067	1060	0.999	0.998	
$n_{C'}$	643.85	1.87758	<b>着色度 Color Code</b>				1000	0.999	0.998	
$n_{He-Ne}$	632.8	1.87853	$\lambda_{80}/\lambda_5$				950	0.999	0.998	
$n_D$	589.29	1.88281	$\lambda_{70}/\lambda_5$		390/340		900	0.999	0.998	
$n_d$	587.56	1.88300	<b>热性质 Thermal Properties</b>				850	0.999	0.998	
$n_e$	546.07	1.88815	$T_g$ (°C)		735		800	0.996	0.993	
$n_F$	486.13	1.89821	$T_s$ (°C)		771		700	0.996	0.993	
$n_{F'}$	479.99	1.89948	$T_{10}^{14.5}$ (°C)		691		650	0.996	0.993	
$n_g$	435.83	1.91054	$T_{10}^{13}$ (°C)		723		600	0.997	0.994	
$n_h$	404.66	1.92103	$T_{10}^{7.6}$ (°C)		830		550	0.997	0.994	
$n_i$	365.01	1.93949	$\alpha_{30/70^\circ C}$ (10 <sup>-7</sup> /K)		68		500	0.992	0.985	
$n_{313.18}$	313.18		$\alpha_{100/300^\circ C}$ (10 <sup>-7</sup> /K)		84		480	0.989	0.979	
$n_{302.15}$	302.15		$\lambda[W/(m \cdot K)]$				460	0.985	0.971	
<b>色散公式常数 Constants of Dispersion Formula</b>							440	0.978	0.957	
$A_0$	3.4341826E+00						420	0.969	0.939	
$A_1$	-1.0619954E-02						400	0.946	0.894	
$A_2$	4.0004630E-02						390	0.921	0.849	
$A_3$	-6.3794224E-04						380	0.879	0.772	
$A_4$	2.1635303E-04						370	0.804	0.647	
$A_5$	-8.4987645E-06						360	0.671	0.450	
<b>折射率温度系数常数 Constants of dn/dt</b>							350	0.447	0.200	
$D_0$	3.45E-07						340	0.173	0.030	
$D_1$	1.47E-08						330			
$D_2$	-7.21E-11						320			
$E_0$	7.69E-07						310			
$E_1$	2.19E-10						300			
$\lambda_{TK}(\mu m)$	0.208						290			
							280			
<b>折射率温度系数 Temperature Coefficients of Refractive Index</b>							<b>机械性质 Mechanical Properties</b>			
<b>温度范围 (°C)</b>		<b>dn/dt relative(10<sup>-6</sup>/°C)</b>						$H_k$ (10 <sup>7</sup> Pa)	741	
<b>Range of Temperature</b>		<b>t</b>	<b>C'</b>	<b>d</b>	<b>e</b>	<b>F'</b>	<b>g</b>	$F_A$	93	
-60~-40								$E$ (10 <sup>7</sup> Pa)	12728	
-40~-20		2.3	2.5	3.0	3.7	4.3	4.6	$G$ (10 <sup>7</sup> Pa)	4886	
-20~0		2.0	3.0	3.4	4.1	4.4	5.2	$\mu$	0.302	
0~20		2.1	3.3	3.6	3.9	4.9	5.7	$B$ (10 <sup>-12</sup> /Pa)	1.00	
20~40		2.4	3.4	3.8	4.0	4.9	5.9	<b>其他性质 Other Properties</b>		
40~60		2.8	3.6	4.1	4.3	4.9	5.9	$\rho$ (g/cm <sup>3</sup> )	5.53	
60~80		2.7	3.5	3.8	4.1	5.1	6.0	<b>备注 Remarks</b>		
80~100										
100~120										
120~140										