

H-ZPK2A			603655		n <sub>d</sub> = 1.60300		v <sub>d</sub> = 65.47		n <sub>F</sub> - n <sub>C</sub> = 0.009210														
					n <sub>e</sub> = 1.60520		v <sub>e</sub> = 65.15		n <sub>F'</sub> - n <sub>C'</sub> = 0.009290														
折射率 Refractive Index			相对部分色散 Relative Partial Dispersions				内部透射率 Internal Transmittance T																
	λ (nm)		P <sub>s,t</sub>	0.2834	P' <sub>s,t</sub>	0.2809	λ (nm)	τ (5mm)	τ (10mm)														
n <sub>2325.42</sub>	2325.42		P <sub>C,s</sub>	0.5451	P' <sub>C',s</sub>	0.5877	2400	0.922	0.850														
n <sub>1970.09</sub>	1970.09		P <sub>d,C</sub>	0.3051	P' <sub>d,C'</sub>	0.2551	2200	0.943	0.889														
n <sub>1529.58</sub>	1529.58		P <sub>e,d</sub>	0.2389	P' <sub>e,d</sub>	0.2368	2000	0.971	0.943														
n <sub>1060.0</sub>	1060.0		P <sub>g,F</sub>	0.5407	P' <sub>g,F'</sub>	0.4801	1800	0.985	0.970														
n <sub>t</sub>	1013.98	1.59256	P <sub>i,h</sub>		P' <sub>i,h</sub>		1600	0.995	0.990														
n <sub>s</sub>	852.11	1.59517	异常色散 Abnormal Dispersions				1400	0.998	0.997														
n <sub>r</sub>	706.52	1.59858					ΔP <sub>C,t</sub>	-0.0263	ΔP <sub>C,s</sub>	-0.0115	1200	0.999	0.998										
n <sub>C</sub>	656.27	1.60019	ΔP <sub>F,e</sub>	0.0020	ΔP <sub>g,F</sub>	0.0065	1060	0.999	0.998														
n <sub>C'</sub>	643.85	1.60063	着色度 Color Code				1000	0.999	0.998														
n <sub>He-Ne</sub>	632.8	1.60105					λ <sub>80</sub> /λ <sub>5</sub>	355/305			950	0.999	0.998										
n <sub>D</sub>	589.29	1.60292	λ <sub>70</sub> /λ <sub>5</sub>				900	0.999	0.998														
n <sub>d</sub>	587.56	1.60300	热性质 Thermal Properties				850	0.999	0.998														
n <sub>e</sub>	546.07	1.60520					T <sub>g</sub> (°C)	619			800	0.999	0.998										
n <sub>F</sub>	486.13	1.60940	T <sub>s</sub> (°C)	648			700	0.998	0.997														
n <sub>F'</sub>	479.99	1.60992	T <sub>10</sub> <sup>14.5</sup> (°C)	563			650	0.998	0.997														
n <sub>g</sub>	435.83	1.61438	T <sub>10</sub> <sup>13</sup> (°C)	595			600	0.998	0.997														
n <sub>h</sub>	404.66	1.61850	T <sub>10</sub> <sup>7.6</sup> (°C)	699			550	0.998	0.997														
n <sub>i</sub>	365.01	1.62550	α <sub>30/70</sub> (10 <sup>-7</sup> /K)	93			500	0.997	0.995														
n <sub>313.18</sub>	313.18		α <sub>100/300</sub> (10 <sup>-7</sup> /K)	115			480	0.997	0.994														
n <sub>302.15</sub>	302.15		λ[W/(m·K)]				460	0.996	0.993														
色散公式常数 Constants of Dispersion Formula			化学性质 Chemical Properties				机械性质 Mechanical Properties																
												A <sub>0</sub>	2.5307319E+00		Grade		H <sub>k</sub> (10 <sup>7</sup> Pa)		382				
												A <sub>1</sub>	-8.3442991E-03		D <sub>w</sub>	1		F <sub>A</sub>		273			
												A <sub>2</sub>	1.4655185E-02		D <sub>A</sub>	4		E (10 <sup>7</sup> Pa)		6814			
												A <sub>3</sub>	-2.1664739E-04		CR	1		G (10 <sup>7</sup> Pa)		2651			
												A <sub>4</sub>	5.3552539E-05		RC(S)	3		μ		0.285			
												A <sub>5</sub>	-2.4615826E-06		RA(S)	1		B (10 <sup>-12</sup> /Pa)		1.10			
折射率温度系数常数 Constants of dn/dt			折射率温度系数 Temperature Coefficients of Refractive Index				其他性质 Other Properties																
												温度范围 (°C)		dn/dt relative(10 <sup>-6</sup> /°C)					ρ (g/cm <sup>3</sup> )		3.50		
												Range of Temperature		t	C'	d	e	F'	g	备注 Remarks			
												-60~-40		-4.1	-3.9	-3.8	-3.6	-3.5	-3.2				
												-40~-20		-4.2	-3.9	-3.8	-3.7	-3.5	-3.4				
												-20~0		-4.2	-3.8	-3.8	-3.7	-3.4	-3.4				
												0~20		-4.2	-3.8	-3.7	-3.7	-3.4	-3.3				
												20~40		-4.2	-3.8	-3.7	-3.6	-3.5	-3.2				
												40~60		-4.1	-3.8	-3.7	-3.6	-3.4	-3.2				
												60~80		-4.1	-3.8	-3.7	-3.6	-3.4	-3.0				
80~100		-4.0	-3.8	-3.6	-3.6	-3.3	-3.0																
100~120		-3.9	-3.7	-3.6	-3.5	-3.2	-2.9																
120~140		-3.9	-3.7	-3.6	-3.4	-3.1	-2.9																