

QF50			581409				n _d = 1.581440		v _d = 40.89		n _F - n _C = 0.014221	
							n _e = 1.584815		v _e = 40.61		n _{F'} - n _{C'} = 0.014400	
折射率 Refractive Index			相对部分色散 Relative Partial Dispersions				内部透射率 Internal Transmittance T					
	λ (nm)		P _{s,t}	0.2410	P' _{s,t}	0.2380	λ (nm)	τ (5mm)	τ (10mm)			
n _{2325.42}	2325.42	1.549465	P _{C,s}	0.4991	P' _{C',s}	0.5388	2400	0.880	0.770			
n _{1970.09}	1970.09	1.554326	P _{d,C}	0.2960	P' _{d,C'}	0.2464	2200	0.911	0.830			
n _{1529.58}	1529.58	1.559692	P _{e,d}	0.2373	P' _{e,d}	0.2344	2000	0.955	0.912			
n _{1060.0}	1060.0	1.565921	P _{g,F}	0.5742	P' _{g,F'}	0.5087	1800	0.981	0.963			
n _t	1013.98	1.566706	P _{i,h}	0.8839	P' _{i,h}	0.8729	1600	0.997	0.995			
n _s	852.11	1.570133	异常色散 Abnormal Dispersions				1400	0.999	0.998			
n _r	706.52	1.574888					ΔP _{C,t}	0.0011	ΔP _{C,s}	0.0007	1200	0.999
n _C	656.27	1.577230	ΔP _{F,e}	-0.0006	ΔP _{g,F}	-0.0018	1060	0.999	0.998			
n _{C'}	643.85	1.577892	着色度 Color Code				1000	0.999	0.998			
n _{He-Ne}	632.8	1.578514					λ ₈₀ /λ ₅	340/310		950	0.999	0.998
n _D	589.29	1.581315	λ ₇₀ /λ ₅			900	0.999	0.998				
n _d	587.56	1.581440	热性质 Thermal Properties				850	0.998	0.997			
n _e	546.07	1.584815					T _g (°C)	422		800	0.998	0.996
n _F	486.13	1.591451	T _s (°C)	480		700	0.998	0.996				
n _{F'}	479.99	1.592292	T ₁₀ ^{14.5} (°C)	366		650	0.997	0.995				
n _g	435.83	1.599617	T ₁₀ ¹³ (°C)	406		600	0.997	0.995				
n _h	404.66	1.606642	T ₁₀ ^{7.6} (°C)	584		550	0.997	0.995				
n _i	365.01	1.619212	α _{30/70°C} (10 ⁻⁷ /K)	90		500	0.997	0.994				
n _{313.18}	313.18	1.647936	α _{100/300°C} (10 ⁻⁷ /K)	111		480	0.996	0.993				
n _{302.15}	302.15		λ[W/(m·K)]			460	0.996	0.993				
色散公式常数 Constants of Dispersion Formula			化学性质 Chemical Properties				440	0.996	0.992			
							K ₁	1.31145759E+00		Grade	420	0.995
L ₁	9.88576985E-03		D _w	1		400	0.995	0.991				
K ₂	8.40047425E-01		D _A	1		390	0.994	0.988				
L ₂	1.02880258E+02		CR	2		380	0.992	0.984				
K ₃	1.32407269E-01		RC(S)	3		370	0.990	0.981				
L ₃	4.77527930E-02		RA(S)	1		360	0.986	0.972				
折射率温度系数常数 Constants of dn/dt			机械性质 Mechanical Properties				350	0.975	0.950			
							D ₀	-2.74E-06		H _k (10 ⁷ Pa)	407	
D ₁	1.64E-08		D _w	1		330	0.850	0.720				
D ₂	-5.12E-11		D _A	1		320	0.570	0.320				
E ₀	8.26E-07		CR	2		310	0.120	0.020				
E ₁	4.87E-10		RC(S)	3		300						
λ _{TK} (μm)	0.234		RA(S)	1		290						
折射率温度系数 Temperature Coefficients of Refractive Index			其他性质 Other Properties				B (10 ⁻¹² /Pa)					
							H _k (10 ⁷ Pa)	407		备注 Remarks		
温度范围 (°C)			dn/dt relative(10 ⁻⁶ /°C)				F _A	89				
							E (10 ⁷ Pa)	5980				
Range of Temperature			t				G (10 ⁷ Pa)	2444				
							μ	0.224				
-60~-40			0.1				B (10 ⁻¹² /Pa)					
-40~-20			0.2									
-20~0			0.3									
0~20			0.6									
20~40			0.7									
40~60			0.8									
60~80			0.8									
80~100			0.8									
100~120			0.8									
120~140			0.8									