

QF6		532488		n _d = 1.53172		v _d = 48.76		n _F - n _C = 0.010905	
				n _e = 1.53431		v _e = 48.48		n _{F'} - n _{C'} = 0.011022	
折射率 Refractive Index			相对部分色散 Relative Partial Dispersions				内部透射率 Internal Transmittance T		
	λ (nm)		P _{s,t}		P' _{s,t}		λ (nm)	τ (5mm)	τ (10mm)
n _{2325.42}	2325.42		P _{C,s}		P' _{C',s}		2400	0.870	0.750
n _{1970.09}	1970.09		P _{d,C}	0.2999	P' _{d,C'}	0.2498	2200	0.900	0.810
n _{1529.58}	1529.58		P _{e,d}	0.2378	P' _{e,d}	0.2353	2000	0.950	0.902
n _{1060.0}	1060.0		P _{g,F}	0.5603	P' _{g,F'}	0.4968	1800	0.979	0.958
n _t	1013.98		P _{i,h}		P' _{i,h}		1600	0.996	0.993
n _s	852.11		异常色散 Abnormal Dispersions				1400	0.997	0.995
n _r	706.52	1.52661	ΔP _{C,t}		ΔP _{C,s}		1200	0.998	0.996
n _C	656.27	1.52845	ΔP _{F,e}	-0.0008	ΔP _{g,F}	-0.0024	1060	0.999	0.998
n _{C'}	643.85	1.52897	着色度 Color Code				1000	0.998	0.996
n _{He-Ne}	632.8	1.52945	λ ₈₀ /λ ₅		330/300		950	0.998	0.997
n _D	589.29	1.53162	λ ₇₀ /λ ₅				900	0.998	0.996
n _d	587.56	1.53172	热性质 Thermal Properties				850	0.997	0.995
n _e	546.07	1.53431	T _g (°C)		436		800	0.998	0.997
n _F	486.13	1.53935	T _s (°C)		504		700	0.998	0.996
n _{F'}	479.99	1.53999	T ₁₀ ^{14.5} (°C)		384		650	0.997	0.995
n _g	435.83	1.54546	T ₁₀ ¹³ (°C)		427		600	0.997	0.995
n _h	404.66	1.55064	T ₁₀ ^{7.6} (°C)		82		550	0.997	0.994
n _i	365.01	1.55972	α _{30/70} (10 ⁻⁷ /K)		98		500	0.996	0.993
n _{313.18}	313.18		α _{100/300} (10 ⁻⁷ /K)				480	0.996	0.992
n _{302.15}	302.15		λ[W/(m·K)]				460	0.995	0.991
色散公式常数 Constants of Dispersion Formula			化学性质 Chemical Properties				440	0.995	0.990
A ₀	2.3044884E+00		Grade				420	0.995	0.990
A ₁	-8.3782321E-03		D _w				400	0.995	0.990
A ₂	1.4424342E-02		D _A				390	0.994	0.988
A ₃	3.3374311E-04		CR				380	0.992	0.985
A ₄	-4.4657456E-06		RC(S)				370	0.992	0.985
A ₅	1.3349929E-06		RA(S)				360	0.989	0.979
折射率温度系数常数 Constants of dn/dt			机械性质 Mechanical Properties				350	0.984	0.968
D ₀			Grade				340	0.969	0.938
D ₁			D _w				330	0.927	0.860
D ₂			D _A				320	0.810	0.650
E ₀			CR				310	0.480	0.230
E ₁			RC(S)				300		
λ _{TK} (μm)			RA(S)				290		
折射率温度系数 Temperature Coefficients of Refractive Index			其他性质 Other Properties				280		
温度范围 (°C)			dn/dt relative(10⁻⁶/°C)				H_k (10⁷Pa)		
Range of Temperature			t	C'	d	e	F'	g	400
-60~-40									F _A
-40~-20									82
-20~0									E (10 ⁷ Pa)
0~20									6237
20~40									G (10 ⁷ Pa)
40~60									2576
60~80									μ
80~100									0.210
100~120									B (10 ⁻¹² /Pa)
120~140									
			备注 Remarks						