





氧化锡电极



质量要求、技术标准:
 $\text{SnO}_2 \geq 97\%$; 显气孔率: 1%;
 容重: $6.6/\text{cm}^3$;
 冷压强度 > 300 ;
 最高使用温度: 1650°C ;
 电阻率 $1000^\circ\text{C}: 4 \times 10^{-3}$

注: 电极组装等编织带, 未在图中显示

数量: 92块

规格: 2050729

制图
审核
审批

订货数量

单位: 块
mm